

HI-BOND WB60

DESCRIPTION

WB60 is a water dispersable epoxy floor and wall coating, having excellent hardwearing and durable qualities, combined with ease of application and maintenance.

ADVANTAGES

Good abrasion resistance. Low odour - ideal for food processing areas

Available in a wide range of colours. Low cost
Easy to apply. Gives a smooth, semi gloss, easy to clean surface.

USES

WB60 is ideal for warehouses, food processing areas and other areas for light vehicular and pedestrian traffic.

TECHNICAL DATA

S.G. (at 15.5°C)	1.17
Solids (by weight)	67.7%
Film Thickness	130 microns @ 5 sq.m per litre
Pot Life (at 20°C)	2 hours
Application Temperature	5°C to 30°C
Overcoating interval	24 hours
Initial Hardness (at 20°C)	24 hours
Full cure (at 20°C)	7days
Recommended No. of coat	2

SURFACE PREPARATION

Substrates should be free from all types of contamination i.e. dirt, grease, oils, fats and laitence. Cleaning should preferably be by shot blasting or mechanical abrading or controlled hot compressed air.

PRIMING

WB61 should be used. It provides maximum adhesion and is supplied in a two part pack of resin and hardener. Apply by brush or roller ensuring a continuous film. Avoid puddles and over application. Very porous substrates may require two coats of primer.

MIXING AND APPLICATION

The WB60 part B curing agent should be added to the part A resin, taking care to remove all resin from the container and mixed for at least 2 minutes until completely homogeneous. Apply the WB60 to the primed floor or wall using a brush or roller. Two coats of the WB60 are normally required for long term protection and to give the required film thickness. Clean all tools with water.

COVERAGE

Approximately 5 sq.m per litre depending on the substrate.

PACKAGING

WB60 is supplied in 5 litre units.

STORAGE

Store between 5°C and 30°C

HEALTH AND SAFETY (see separate health & safety data sheet)

Wear gloves and protective clothing when using WB60. In case of contact with eyes, rinse immediately with plenty of water and seek medical advice. After contact with skin, wash immediately with soap and water.

WARRANTY DISCLAIMER

The technical data herein has been compiled for your help and guidance and is based upon our experience. As we have no control over the use to which our information is put, no warranty, expressed or implied is intended or given and we cannot be held responsible for coverage, performance or any damages incurred.

Hi-bond Chemicals Ltd, Ince, Wigan, Lancs 01942 615800 DATA S/781998
