

HI-BOND EC5LM

DESCRIPTION

EC5LM is a solvent based, high gloss, high performance two pack epoxy coating having good abrasion and chemical resistance. Ideal for floors, walls and line markings.

ADVANTAGES

Hard, tough and abrasion resistant, good chemical resistance, impervious finish ensures ease of cleaning and excellent adhesion to cementitious substrates etc.

TYPICAL PROPERTIES

Solids	70.0%
Flash point	29°C
Recommended dry film thickness (DFT)	60 microns per coat
Volume Solids	60%
Theoretical coverage	10m ² /litre to give 60 microns DFT
S.G.(Mixed)	1.14
Pot Life (at 20°C)	60 minutes
Drying Times (at 20°C)	Touch dry: 1 hour. Hard: 8 hours.
Full cure (at 20°C)	7 days
Overcoating time	Min: 30 minutes. Max: 2 days
Recommended No. of coats	2

CHEMICAL RESISTANCE

Excellent against aqueous media, dilute acids, alkalis, moderate resistance against alcohols and certain chlorinated hydrocarbons.

SURFACE PREPARATION

The efficiency of the EC5 is dependant on the preparation of the substrate.

Substrates should be free from all types of contamination i.e. dirt, grease, oils, fat and laitence. Cleaning should preferably be by shot blasting, mechanical abrading or controlled hot compressed air.

MIXING AND APPLICATION

Add the contents of Part "B" to Part "A" and mix thoroughly. Failure to mix thoroughly could result in poor or non-cure material. Apply immediately by brush or roller.

STORAGE

Store in sealed containers between 5°C and 35°C.

PACKAGING

EC5LM is a two pack epoxy system packed in 5 litre units.

CLEANING

HiSolve should be used for cleaning tools, etc.

HEALTH AND SAFETY

See separate Health and Safety Data Sheet.

WARRANTY DISCLAIMER

The technical data herein has been compiled for your help and guidance and is based upon our experience. As we have no control over the use to which our information is put, no warranty, expressed or implied is intended or given and we cannot be held responsible for coverage, performance or any damages incurred.

Hi-bond Chemicals Ltd, Ince, Wigan, Lancs 01942 615800 DATA S/781998
